

EcoTPE

2K 90

Specifications


Excellent for overmoulding with adhesion to PP and PE

- Recycled Thermoplastic Elastomers (TPS-SEBS)
- 30 % Recycled Content
- Pellets with Black Colour


Processing

- **Pre-Drying** is generally not necessary but can be carried out for 3-4 h at 70 °C.
- **Cylinder Temperature:** Injection moulding recommended with 180-210 °C barrel temperature.
- **Mould Temperature:** 30-60 °C recommended mould temperature.

In short



Recycled
Thermoplastic
Elastomers



Black Colour
Pellets

30 %

Amount of re-
cycled content

	Hardness	Tensile Strength	Stress at 100% Strain	Stress at 300% Strain	Elongation at break	Tear Strength
	ISO 868 Shore A	ISO 37 MPa	ISO 37 MPa	ISO 37 MPa	ISO 37 %	ISO 34 kN/m
EcoTPE 2K 90	85	9.1	4.5	6.3	540	19

Injection moulding guide

For EcoTPE

Plasticising: Complete the plasticising just prior the start of the next cycle. Adjust the screw speed and backpressure to obtain the desired melt temperature. The screw speed depends on the diameter of the screw. Contact the material supplier for more support regarding plasticising and screw speeds.

Decompression: 5-15 mm.

Injection Pressure: Overfilling and overheating can occur when too high injection pressures are used. To avoid the above-mentioned defects, use the minimal injection pressure required for a uniform filling of the mould.

Injection Rate: EcoTPE exhibit shear thinning that reduces the viscosity by increasing the share rate. Thus, for filling the mould moderate to fast injections rates are necessary dependent on the part size.

Holding phase: It is recommended to optimize the holding pressure and holding time to avoid defects like overfilling and shrink marks. Overfilling is more common for soft materials like thermoplastic elastomers. Thus, the holding pressure should be as low as possible to avoid this defect, especially for the softer grades. In addition, it is advantageous to use a small material cushion of about 5 mm.

Venting of the mould is required to avoid air inclusions because moderate/high injection rates are used during injection moulding of EcoTPE.

Clamping Force: There is generally no need to apply a high clamping force for EcoTPE. A clamping force of 2.5-5 kN/cm² projected area of the moulded part is recommended.

Cooling Time: Generally, cooling times of 15-25 s is sufficient for parts up to 2 mm thickness and longer cooling times with increasing thickness of the moulded parts.

Legal disclaimer

Legal disclaimer and notice to users

This document or publication was printed based on Ecorub's present state of knowledge, and Ecorub undertakes no obligation to update it. Because conditions of product use are outside Ecorub's control, Ecorub makes no warranties, expressed or implied, and assumes no liability in connection with any use of this information. Nothing herein is intended as a license to operate under or a recommendation to infringe any patents.

The values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their product use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use and entrust the handling of such material to adequately trained personnel only. The products mentioned herein are not intended for use in medical or dental implants.

Ecorub®, registered design and trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Ecorub AB.

© 2024 Ecorub AB. All rights reserved. Published January 2024.